

### **Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application.

#### **Listing of Claims:**

1.     **(Currently Amended)** A flexible multi-layer medium comprising:  
a flexible support layer having a first side and a second side;  
a flexible antimicrobial layer adjacent said first side of said support layer; and  
a flexible adhesive layer having a top side adjacent said second side of said support layer for adhering to the support layer, and having a bottom side for adhering to a surface, wherein the antimicrobial layer is secured to the surface via the support layer and the adhesive layer and is uncovered for providing an exposed bactericidal surface.
2.     **(Currently Amended)** ~~A medium according to claim 1~~ A flexible multi-layer medium comprising:  
a flexible support layer having a first side and a second side;  
a flexible antimicrobial layer adjacent said first side of said support layer;  
a flexible adhesive layer adjacent said second side of said support layer; and  
wherein said antimicrobial layer changes color as the effectiveness of said antimicrobial is reduced.
3.     **(Withdrawn)** A medium according to claim 1 wherein said antimicrobial layer provides a controlled release of a antimicrobial material.
4.     **(Withdrawn)** A medium according to claim 3 wherein said controlled release is accomplished by use of a diffusion layer placed over said antimicrobial layer.

5. **(Withdrawn)** A medium according to claim 3 wherein said antimicrobial material comprises an antimicrobial metal ion exchange material which is exchanged with at least one colored metal ion or colored metal ion complex.

6. **(Withdrawn)** A medium according to claim 5 wherein said antimicrobial metal ion is selected from one of the following:

silver  
gold  
copper  
zinc  
nickel

7. **(Withdrawn)** A medium according to claim 1 wherein a colored material is provided in said medium that has a diffusion rate substantially the same as the depletion rate of the active ingredient in said antimicrobial layer so that a visual indication will be provided as to the effectiveness of said active ingredient.

8. **(Withdrawn)** A medium according to claim 1 wherein the color change is about equal or greater than a 0.2 change in optical density.

9. **(Withdrawn)** A medium according to claim 8 where the color change is greater than a 0.5 change in optical density.

10. **(Withdrawn)** A medium according to claim 1 wherein the antimicrobial layer is made from one or more of the following antimicrobial compounds:

silver sodium zirconium phosphate  
silver zeolite  
or silver ion exchange resins,  
benzoic acid, sorbic acid, nisin, thymol, allicin, peroxides, imazalil, triclosan,  
benomyl, metal-ion release agents, metal colloids, anhydrides, and organic quaternary ammonium salts.

11. **(Currently Amended)** A medium according to claim 1 wherein the support layer is made from one or more of the following:

resin-coated paper;  
paper, polyesters;  
micro porous materials;  
polyethylene;  
plain paper;  
coated paper;  
synthetic paper;  
photographic paper support;  
melt-extrusion-coated paper;  
laminated paper;  
biaxially oriented polyolefin;  
polypropylene;  
glass;  
cellulose derivatives; and  
polyesters.

12. **(Currently Amended)** ~~A medium according to claim 1~~  
flexible multi-layer medium comprising:  
a flexible support layer having a first side and a second side;  
a flexible antimicrobial layer adjacent said first side of said support  
layer;  
a flexible adhesive layer adjacent said second side of said support  
layer;

wherein the adhesive layer is made from one or more of the following:  
reposition adhesive; and  
flexible static-cling vinyl.

13. **(Currently Amended)** ~~A medium according to claim 1~~ A flexible multi-layer medium comprising:  
a flexible support layer having a first side and a second side;  
a flexible antimicrobial layer adjacent said first side of said support  
layer;  
a flexible adhesive layer adjacent said second side of said support  
layer; and

wherein the diffusion layer comprises a dye which diffuses from the diffusion layer when the sheet is exposed to a biological environment.

14. **(Original)** A medium according to claim 1 wherein the antimicrobial layer has a thickness in the range of .01  $\mu\text{m}$  to 100  $\mu\text{m}$ .

15. **(Original)** A medium according to claim 1 where the thickness of said antimicrobial layer is about 5  $\mu\text{m}$ .

16. **(Original)** A medium according to claim 1 wherein the support layer has a thickness in the range of 0.025 mm to 5 mm.

17. **(Original)** A medium according to claim 1 where the thickness of said support layer is about 0.125 mm.

18. **(Original)** A medium according to claim 4 wherein the diffusion layer has a thickness in the range of 0.2  $\mu\text{m}$  to 25  $\mu\text{m}$ .

19. **(Original)** A medium according to claim 4 where the thickness of said diffusion layer is about 5  $\mu\text{m}$ .

20. **(Original)** A medium according to claim 1 further comprising a subbing layer provided between support layer and said antimicrobial layer for providing proper adhesion of the antimicrobial layer to said support layer.

21. **(Original)** A medium according to claim 1 wherein a removable protective layer is provided over said adhesive layer for protecting said adhesive layer until it can be secured to a receiving surface.

22. **(Original)** A multi-layer medium comprising:  
a support layer having a first side and a second side;  
a antimicrobial layer adjacent said first side of said support layer, said antimicrobial layer having an indicating means for providing a visual indication of the effectiveness of the antimicrobial layer; and  
an adhesive layer adjacent said second side of said support layer.

23. **(Original)** A multi-layer medium according to claim 22 wherein said visual indication means comprises a change in color when the effectiveness of said antimicrobial is reduced.

24. **(Original)** A medium according to claim 22 wherein said antimicrobial layer provides a controlled release of a antimicrobial material.

25. **(Original)** A medium according to claim 24 wherein said controlled release is accomplished by use of a diffusion layer placed over said antimicrobial layer.

26. **(Original)** A medium according to claim 24 wherein said antimicrobial material comprises an antimicrobial metal ion which is exchanged with at least one colored metal ion or colored metal ion complex.

27. **(Currently Amended)** A medium according to claim 26 wherein said antimicrobial metal ion is selected from one of the following:

silver;  
gold;  
copper;  
zinc; or  
nickel.

28. **(Original)** A medium according to claim 22 wherein a colored material is provided in said medium that has a diffusion rate substantially the same as the depletion rate of the active ingredient in said antimicrobial layer so that a visual indication will be provided as to the effectiveness of said active ingredient.

29. **(Original)** A medium according to claim 23 wherein the color change is about equal or greater than a 0.2 change in optical density.

30. **(Original)** A medium according to claim 29 where the color change is greater than a 0.5 change in optical density.

31. **(Currently Amended)** A medium according to claim 22 wherein the antimicrobial layer is made from one or more of the following antimicrobial compounds:

silver sodium zirconium phosphate;

silver zeolite;

or silver ion exchange resins;

benzoic acid, sorbic acid, nisin, thymol, allicin, peroxides, imazalil, triclosan, benomyl, metal-ion release agents, metal colloids, anhydrides, and organic quaternary ammonium salts.

32. **(Currently Amended)** A medium according to claim 22 wherein the support layer is made from one or more of the following:

resin-coated paper;

paper, polyesters;

micro porous materials;

polyethylene;

plain paper;

coated paper;

synthetic paper;

photographic paper support;

melt-extrusion-coated paper;

laminated paper;

biaxially oriented polyolefin;

polypropylene;  
glass;  
cellulose derivatives; or  
polyesters.

33. **(Currently Amended)** A medium according to claim 22 wherein the adhesive layer is made from one or more of the following:

reposition adhesive; or  
flexible static-cling vinyl.

34. **(Original)** A medium according to claim 25 wherein the diffusion layer comprises a dye which diffuses from the diffusion layer when the sheet is exposed to a biological environment.

35. **(Original)** A medium according to claim 22 wherein the antimicrobial layer has a thickness in the range of .01  $\mu\text{m}$  to 100  $\mu\text{m}$ .

36. **(Original)** A medium according to claim 22 where the thickness of said antimicrobial layer is about 5  $\mu\text{m}$ .

37. **(Original)** A medium according to claim 22 wherein the support layer has a thickness in the range of 0.025 mm to 5 mm.

38. **(Original)** A medium according to claim 22 wherein the thickness of said support layer is about 0.125 mm..

39. **(Original)** A medium according to claim 26 wherein the diffusion layer has a thickness in the range of 0.2  $\mu\text{m}$  to 25  $\mu\text{m}$ .

40. **(Original)** A medium according to claim 26 where the thickness of said diffusion layer is about 5  $\mu\text{m}$ .

41. **(Original)** A medium according to claim 22 further comprising a subbing layer provided between support layer and said antimicrobial layer for providing proper adhesion of the antimicrobial layer to said support layer.

42. **(Original)** A medium according to claim 22 wherein a removable protective layer is provided over said adhesive layer for protecting said adhesive layer until it can be secured to a receiving surface.

43. **(Withdrawn)** A antimicrobial medium having a visual indicator for indicating the loss of effectiveness of the antimicrobial medium.

44. **(Withdrawn)** A medium according to claim 43 wherein said antimicrobial medium changes color as the effectiveness of said antimicrobial is reduced.

45. **(Withdrawn)** A medium according to claim 43 wherein said antimicrobial medium provides a controlled release of a antimicrobial material.

46. **(Withdrawn)** A medium according to claim 45 wherein said controlled release is accomplished by use of a diffusion layer placed over said antimicrobial layer.

47. **(Withdrawn)** A medium according to claim 46 wherein said antimicrobial material comprises a antimicrobial metal ion which is exchanged with at least one colored metal ion or colored metal ion complex.



48. **(Withdrawn)** A medium according to claim 46 wherein said antimicrobial metal ion is selected from one of the following:

silver  
gold  
copper  
zinc  
nickel

49. **(Withdrawn)** A medium according to claim 43 wherein a colored material is provided in said medium that has a diffusion rate substantially the same as the depletion rate of the active ingredient in said antimicrobial medium so that a visual indication will be provided as to the effectiveness of said active ingredient.

50. **(Withdrawn)** A medium according to claim 43 wherein the color change is about equal or greater than a 0.2 change in optical density.

51. **(Withdrawn)** A medium according to claim 50 where the color change is greater than a 0.5 change in optical density.

52. **(Withdrawn)** A medium according to claim 43 wherein the antimicrobial medium is made from one or more of the following antimicrobial compounds:

silver sodium zirconium phosphate  
silver zeolite  
or silver ion exchange resins,  
benzoic acid, sorbic acid, nisin, thymol, allicin, peroxides, imazalil, triclosan,  
benomyl, metal-ion release agents, metal colloids, anhydrides, and organic quaternary ammonium salts.

53. **(Withdrawn)** A medium according to claim 43 wherein the antimicrobial medium has a thickness in the range of .01  $\mu\text{m}$  to 100  $\mu\text{m}$ .

54. **(Withdrawn)** A medium according to claim 43 where the thickness of said antimicrobial medium is about 5  $\mu\text{m}$ .

55. **(Withdrawn)** A medium according to claim 43.

56. **(Currently Amended)** A multi-layer medium comprising:  
a support layer having a first side and a second side;  
an antimicrobial layer adjacent said first side of said support layer having controlled release of the active antimicrobial ingredient in said antimicrobial layer; and  
an adhesive layer having a top side adjacent said second side of said support layer for adhering to the support layer, and having a bottom side for adhering to a surface, wherein the antimicrobial layer is secured to the surface via the support layer and the adhesive layer and is uncovered for providing an exposed bactericidal surface.

57. **(Currently Amended)** ~~A medium according to claim 56~~  
A multi-layer medium comprising:  
a support layer having a first side and a second side;  
an antimicrobial layer adjacent said first side of said support layer  
having controlled release of the active antimicrobial ingredient in said antimicrobial layer; and  
an adhesive layer adjacent said second side of said support layer,  
wherein said antimicrobial layer changes color as the effectiveness of said antimicrobial is reduced.

58. **(Withdrawn)** A medium according to claim 56 wherein said antimicrobial layer provides a controlled release of an antimicrobial material.

59. **(Original)** A medium according to claim 57 wherein said controlled release is accomplished by use of a diffusion layer placed over said antimicrobial layer.

60. **(Original)** A medium according to claim 57 wherein said antimicrobial material comprises a antimicrobial metal ion which is exchanged with at least one colored metal ion or colored metal ion complex.

61. **(Currently Amended)** A medium according to claim 60 wherein said antimicrobial metal ion is selected from one of the following:

silver;

gold;

copper;

zinc, or

nickel.

62. **(Currently Amended)** ~~A medium according to claim 56~~

A multi-layer medium comprising:

a support layer having a first side and a second side;

an antimicrobial layer adjacent said first side of said support layer having controlled release of the active antimicrobial ingredient in said antimicrobial layer; and

an adhesive layer adjacent said second side of said support layer,

wherein a colored material is provided in said medium that has a diffusion rate substantially the same as the depletion rate of the active ingredient in said antimicrobial layer so that a visual indication will be provided as to the effectiveness of said active ingredient.

63. **(Currently Amended)** ~~A medium according to claim 56~~

A multi-layer medium comprising:

a support layer having a first side and a second side;

an antimicrobial layer adjacent said first side of said support layer having controlled release of the active antimicrobial ingredient in said antimicrobial layer; and

an adhesive layer adjacent said second side of said support layer,

wherein the color change is about equal or greater than a 0.2 change in optical density.

64. **(Original)** A medium according to claim 63 where the color change is greater than a 0.5 change in optical density.

65. **(Currently Amended)** ~~A medium according to claim 56~~  
A multi-layer medium comprising:  
a support layer having a first side and a second side;  
an antimicrobial layer adjacent said first side of said support layer  
having controlled release of the active antimicrobial ingredient in said antimicrobial  
layer; and

an adhesive layer adjacent said second side of said support layer,  
wherein the antimicrobial layer is made from one or more of the following  
antimicrobial metal ion compounds:

silver sodium zirconium phosphate;  
silver zeolite; or  
~~or~~ silver ion exchange resins, benzoic acid, sorbic acid, nisin, thymol,  
allicin, peroxides, imazalil, triclosan, benomyl, metal-ion release agents, metal  
colloids, anhydrides, and organic quaternary ammonium salts.

66. **(Currently Amended)** A medium according to claim 56  
wherein the support layer is made from one or more of the following:

resin-coated paper;  
paper, polyesters;  
micro porous materials;  
polyethylene;  
plain paper;  
coated paper;  
synthetic paper;  
photographic paper support;  
melt-extrusion-coated paper;  
laminated paper;  
biaxially oriented polyolefin;

polypropylene;  
glass;  
cellulose derivatives; or  
polyesters.

67. **(Currently Amended)** ~~A medium according to claim 56~~  
A multi-layer medium comprising:  
a support layer having a first side and a second side;  
a antimicrobial layer adjacent said first side of said support layer  
having controlled release of the active antimicrobial ingredient in said antimicrobial  
layer; and  
an adhesive layer adjacent said second side of said support layer,  
wherein the adhesive layer is made from one or more of the following:  
reposition adhesive;  
flexible static-cling vinyl.

68. **(Original)** A medium according to claim 56 wherein the diffusion layer comprises a dye which diffuses from the diffusion layer when the sheet is exposed to a biological environment.

69. **(Original)** A medium according to claim 56 wherein the antimicrobial layer has a thickness in the range of 0.1  $\mu\text{m}$  to 25  $\mu\text{m}$ .

70. **(Original)** A medium according to claim 56 wherein the thickness of said antimicrobial layer is about 5  $\mu\text{m}$ .

71. **(Original)** A medium according to claim 56 wherein the support layer has a thickness in the range of 0.025 mm to 5 mm.

72. **(Original)** A medium according to claim 56 where the thickness of said support layer is about 0.125 mm.

73. **(Original)** A medium according to claim 59 wherein the diffusion layer has a thickness in the range of 0.2  $\mu\text{m}$  to 25  $\mu\text{m}$ .

74. **(Original)** A medium according to claim 59 where the thickness of said diffusion layer is about 5  $\mu\text{m}$ .

75. **(Original)** A medium according to claim 56 further comprising a subbing layer provided between support layer and said antimicrobial layer for providing proper adhesion of the antimicrobial layer to said support layer.

76. **(Original)** A medium according to claim 56 wherein a removable protective layer is provided over said adhesive layer for protecting said adhesive layer until it can be secured to a receiving surface.

77. **(Withdrawn)** An antimicrobial material for detecting exposure to a pathogen, comprising an antimicrobial metal ion exchange material which is exchanged with at least one colored metal ion or colored metal ion complex.

78. **(Withdrawn)** An antimicrobial material according to claim 77 wherein said color of said material indicates the effectiveness of said antimicrobial material.

79. **(Withdrawn)** An antimicrobial material according to claim 77 wherein said antimicrobial material provides a controlled release of a antimicrobial material.

80. **(Withdrawn)** An antimicrobial material according to claim 79 wherein said controlled release is accomplished by use of a diffusion layer placed over said antimicrobial layer.

81. **(Withdrawn)** An antimicrobial material according to claim 77 wherein said antimicrobial metal ion is selected from one of the following:

- silver
- gold
- copper
- zinc
- nickel

82. **(Withdrawn)** An antimicrobial material according to claim 77 wherein the antimicrobial material comprises one or more of the following antimicrobial compounds:

- silver sodium zirconium phosphate
- silver zeolite
- or silver ion exchange resins,

benzoic acid, sorbic acid, nisin, thymol, allicin, peroxides, imazalil, triclosan, benomyl, metal-ion release agents, metal colloids, anhydrides, and organic quaternary ammonium salts.

83. **(Withdrawn)** An antimicrobial material according to claim 77 wherein said material includes a support layer made from one or more of the following:

- resin-coated paper
- paper, polyesters
- micro porous materials
- polyethylene
- plain paper
- coated paper
- synthetic paper
- photographic paper support
- melt-extrusion-coated paper
- laminated paper
- biaxially oriented polyolefin

polypropylene  
glass  
cellulose derivatives  
polyesters.

84. **(Withdrawn)** An antimicrobial material according to claim 77 wherein an adhesive layer is provided which is made from one or more of the following:

reposition adhesive  
flexible static-cling vinyl.

85. **(Currently Amended)** A plurality of flexible multi-layer sheets removably adhered ~~layered~~ together to form a stack of the flexible multi-layer sheets, each sheet ~~medium~~ comprising:

a flexible support layer having a top ~~first~~ side and a bottom ~~second~~ side;

a flexible antimicrobial layer having an antimicrobial top side and an antimicrobial bottom side, the antimicrobial bottom side adjacent said top ~~first~~ side of said support layer; and

a flexible adhesive layer having an adhesive top side adjacent said bottom ~~second~~ side of said support layer, and an adhesive bottom side adjacent an antimicrobial top side of another one of said sheets.

86. **(Currently Amended)** A flexible multi-layer medium comprising:

a flexible support layer having a first side and a second side;

a flexible antimicrobial layer adjacent said first side of said support layer; and

a flexible adhesive layer having a top side adjacent said second side of said support layer for adhering to the support layer, and having a bottom side that can be configured to be adhered to a non flat surface, wherein the antimicrobial layer is secured to the non flat surface via the support layer and the adhesive layer and is uncovered for providing an exposed bactericidal surface for food products.



87. **(Withdrawn)** A method of attaching the flexible multi-layer medium of claim 1 is attached to a surface via the adhesive layer.

88. **(Withdrawn)** A method of claim 87 wherein the antimicrobial material is released in a controlled fashion by use of a diffusion layer placed over said antimicrobial layer.

89. **(Withdrawn)** A method of claim 87 wherein the antimicrobial material is substantially depleted or is substantially no longer effective and is peeled from the surface and replaced with a new sheet of multilayer medium.

90. **(Withdrawn)** The method of claim 87 wherein the antimicrobial material for determining when the antimicrobial properties of the sheet of multilayer medium changes color as the effectiveness of said antimicrobial is reduced.